


DESCRIPTION						
Total Thickness	EN ISO 24346	mm	6.00			
Thickness of the wearlayer	EN ISO 24340	mm	0.55			
Weight	EN ISO 23997	g/m <sup>2</sup>	9480			
Size	EN ISO 24342	mm	177x1219	225x1524	457x914	125 x 750
Number of planks /tiles and sqm per box	-	-	8 / 1.73 m <sup>2</sup>	5 / 1.71 m <sup>2</sup>	4 / 1.67 m <sup>2</sup>	16 / 1.5 m <sup>2</sup>
CLASSIFICATION						
Norm/Product Specification	-	-	EN ISO 10582			
European Classification	EN ISO 10874	class	33 - 42			
Fire Rating	EN 13 501-1	class	Bfl-s1			
Static Electrical Propensity	EN 1815	kV	< 2			
Slip Resistance Wet	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10			
PERFORMANCES						
Wear Resistance	EN 660.2	mm <sup>3</sup>	< 2.0			
Wear Group	-	group	T			
Type binder content	EN ISO 10582	type	I			
Room Impact	NF S 31074	dB	81			
Impact sound insulation	EN ISO 717-2	dB	19			
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15			
Dimensional stability (average measured value)	-	%	≤ 0.05			
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10			
Castor chair test	ISO 4918	-	OK			
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25			
Colour Fastness	EN ISO 105 - B02	degree	≥ 6			
Surface Treatment	-	-	Protecshield™			
Chemical Products Resistance	EN ISO 26987		OK			
ENVIRONMENT / INDOOR AIR QUALITY						
TVOC after 28 days	ISO 16000-6	µg/ m3	< 10			
CE MARKING						
	EN 14041		